

Handling Instruction

Date: 01.06.2005 / Page 1 of 1

Percenta Anti-Condensation for Synthetic Material

Areas of application:

Wind deflector plates of motorbikes, shower partitions, synthetic windows, visors

Percenta Anti-Condensation for Synthetic Materials is a coating material for synthetic surfaces with anti-condensation- and antistatic effect.

Dilution:	None
Quantity to be applied:	approx. 10-15 ml per m ²
Curing/Drying:	approx. 1-2 minutes at least
Processing temperature:	+5°C to +25°C - to be protected against direct insolation -
Handling:	refer to safety data sheet
Storing and durability:	refer to safety data sheet, imprint on bottles or cans
Storing temperature:	+5°C to +25°C, to be protected against direct insolation and frost, to be stored well closed in the original container

Application:

The carrying of gloves is recommended. Percenta Anti-Condensation for Synthetics dehumidifies the skin. The application should be checked at an inconspicuous spot or a sample. Not to be applied at temperatures below +5°C.

Preparation:

The surface has to be cleaned carefully from dusty, greasy and fatty pollutions. It is recommended to use Percenta Synthetic-Cleaner or Glass SR-Cleaner. Then it should be rinsed intensively with clear water. Before coating the surfaces must be clean, dry and non-greasy.

Coating:

Put a small portion of Percenta Anti-Condensation for Synthetic Material on a dry, fluff-free towel and apply it regularly to the surface, so that a closed, thin fluid coat arises, which will dry up slowly.

Drying:

Within a short time period (approx. 1 min) the coating is dry. If after drying reams become visible, too much of the product was used. A repetition of the coating with less coating material takes out the reams and ensures high visibility

Influence of the environment:

Do only coat small surfaces at temperatures above 25°C.

Cleaning of the coated surface:

The surfaces coated with Percenta Anti-Condensation for Synthetic Material can be cleaned with mild cleaners (for example Percenta Glass SR). It is recommended to carry out a re-coating, as described above.

Note:

The present instruction for use is based on extensive researches, but doesn't release the user, to check the product and procedures for suitability for his own special use. Especially we are not responsible for such purposes of application and use which we have not emphasized particularly in writing.

By all means the instructions and notes of the safety data sheets must be taken into consideration.